



		25	30	40	70	
DENSITY UNI EN ISO 845	kg/m ³ ± 5%	25	30	40	70	
COMPRESSION LOAD DEFLECTION UNI EN ISO 3386	kpa ± 15%	5,7	7	8	13	
IDENTATION LOAD DEFLECTION UNI EN ISO 2439	Newton ± 15%	170	210	250	--	
	25% 65%	480	550	665	--	
ELONGATION AT BREAK UNI EN ISO 1798	% min	130	120	100	65	
LOAD AT BREAK (TRACTION) UNI EN ISO 1798	kpa min	120	150	184	--	
TEAR RESISTANCE UNI EN ISO 8067	N/m	250	260	298	--	
RESILIENCE UNI EN ISO 8307	% (± 10%)	40	40	45	--	
DYNAMIC FATIGUE UNI EN ISO 3385	% max	30	30	25	20	
COMPRESSION SET UNI EN ISO 1856/A	% max	3	3	2	2	
	50% 70%	5	4	3	3	
FIRE TESTS		A	A	A	A	
COLOR		○	○	○	on demand	
BLOCKS WIDTH IN CM		215	215	215	140X190 140X200 160X190 180X120 200X210	



SITAB P.E. fire-resistant products have specially predetermined fire reaction characteristics, according to national or international standards, to meet specific use requirements. Each certification of reaction to fire relevant to any product can be downloaded directly from the appropriate section of our website.



Legend of fire resistance certifications

- A – Technical Bulletin 117 – 2013 Section 3 (Californian Test)
- C – The furniture and Furnishings Regulations 1988, S.I. No. 1324, Schedule 1 Part 1
- D – FAR 25.853 (Federal Aviation Regulations)
- E – UNI 9175 (CSE RF 4/83 CLASSE 1 IM) con tessuti idonei
- F – Classement M4
- G – MVSS 302
- H – ABD 0031 – Airbus Industrie (ATS 1000.01 Airbus Test Specification)
- I – UL 94 HF-1 (Horizontal Burning Foamed Material Test)
- L – UNI 10707: 2003 NF F 16-101 (NF X 70-100: 2006)
- M – IMO 2010 – FTP code

Warnings

The data reported in the “technical features/technical data sheets” refer to samples obtained in the perpendicular plane to the growth direction of the product during the reaction phase and not near the external surfaces. High resilience materials such as HR and AT must be previously subjected to mechanical treatments to generate cell breakage (mangling).

We recommend to obtain the desired details so that during the final use phase they are stressed in a parallel direction to the direction of growth.

Data and information contained in this document and in the each technical sheets are based on the knowledge available on the issue’s date or subsequent revisions. SITAB PE reserves the right to modify the data herein reported at any time.

SITAB PE does not guarantee the sufficiency of the recommendations/warnings contained in this document and in each technical data sheets. Furthermore it’s not excluded that further measures may be required in particular or exceptional circumstances.

In case of compressed materials it will be necessary a waiting time of at least 24 hours from the material decompression. The material must be kept compressed for the shortest possible time, ideally just for the time necessary for transport. In the 24 hours following decompression (or at least for a few hours) it is necessary that the blocks/plates are not subjected to pressure from any direction, such as load compression, blocks / plates stacked on one another or pressed against the wall. For viscoelastic materials it is necessary to consider their thermo sensitivity: the ideal temperatures should be higher than 15 degrees. It is also necessary that the support base is sufficiently smooth to allow the material to “slip”, thus facilitating the return.